## **EUROPEAN PATENT OFFICE**

## **Patent Abstracts of Japan**

**PUBLICATION NUMBER** 

: 11244991

PUBLICATION DATE

14-09-99

**APPLICATION DATE** 

26-02-98

APPLICATION NUMBER

10062051

APPLICANT: GUN EI CHEM IND CO LTD;

INVENTOR: MASHIO HITOSHI;

INT.CL.

: B22C 1/22 C09D161/06

TITLE

: MANUFACTURE OF RESIN COATED SAND

ABSTRACT: PROBLEM TO BE SOLVED: To provide a manufacturing method for a resin coated sand for molding a shell mold which is low in odor, high in strength and resistant in blocking property.

> SOLUTION: In a manufacturing method, novolac phenol resin of 0.5-5 pts.wt. is added to a refractory aggregate of 100 pts.wt. heated to 100-180°C is added, melted and kneaded, the novolac phenol resin is uniformly coated on the surface of the refractory aggregate, and resol phenol resin emulsion or suspension of 0.5-5 pts.wt. is added thereto. In addition, the volatile component is evaporated and removed through further kneading, and the resin is coated on the surface of the refractory aggregate.

COPYRIGHT: (C)1999,JPO